




VERNIZ PRONTO PARA USO 7000

Quick Reference


Ready to Spray

Description:

Acrylic clearcoat to be used as a topcoat over Wandabase HS (BRET) or Wanda Acrílico Universal. It can be used for small spot repairs and total resprays. It has a good gloss and polish performance.



14 - 18 sec.

1.2-1.5 mm
3-4 bar

5 - 10 min.

8 a 12h – 25°C
30 min – 60°C**Products and Additives:**

Verniz pronto para uso 7000

Basic Raw Materials:

Acrylic resin, acetatobutyrate, esters, aromatic solvents and additives.

Suitable Substrates:

Wandabase HS (BRET) or Wandabase Acrílico Universal

Surface Preparation:

Following a flash off time of 15-20 minutes Verniz 7000 can be applied over the basecoat.

Mixing Ratio:

Ready to Spray

Spray Viscosity:

14 – 18 seconds FC4 / 25°C

Spray gun fluid tip and working pressure:**Spray Gun:**

Suction Feed:

Gravity Feed:

HVLP:

Fluid tip:

1.8 mm

1.2 – 1.5 mm

1.2 – 1.5 mm

Pressure :3-4 bar (40-50 lb/pol²)3-4 bar (40-50 lb/pol²)3-4 bar (40-50 lb/pol²)**Process:**

Apply 2 cross coats with a time of 5-10 minutes between the coats

Film Thickness:

Approximately 15 - 20 microns per coat.

Observations:

These products are intended for professional use only. Please, refer to can, Technical Data Sheet and Safety Data Sheet form more specific information. These products are thoroughly controlled and their quality will be kept as long as they are used according to the manufacturer recommendations. The final result depending upon factors of use which are outside our control.



Theoretical cover rate : 8 m²/litre per coat
Note: The practical coverage depends on several factors, including shape of the construction, roughness of surface, method of application and conditions of application.

Cleaning of equipment: Use Thinner Wanda 1100 – 407.04000

Drying times:

	25°C	60°C
Dust	5 min	-----
Touch	30 min	-----
Handle	1-2 h	30 min
Total	8 - 12 h	1h at 25°C (after backing)

Shelf life: 3 years at temperatures between 15 and 35°C, no humidity.

Health and Safety data: Please refer to MSDS

Notes:

- The Wandabase should not be sanded before clear application.
- It is recommended to extend the paint in parts spraying.
- Always use the indicated hardener to the product.
- To apply on the hood it is recommended 3 coats to improve the durability due to a higher heat exposure (from engine and from sun).
- The panel can be polished after total drying. Firstly, take of the impurities with a Scot Brite or a soft sand paper, and polish it manual or mechanically.

Observations:

These products are intended for professional use only. Please, refer to can, Technical Data Sheet and Safety Data Sheet form more specific information. These products are thoroughly controlled and their quality will be kept as long as they are used according to the manufacturer recommendations. The final result depending upon factors of use which are outside our control.